

### LIGHTING LUMINAIRE

## **CHELA-26W**

Report No. L70-CHELA-26W

## DIMON TECHNOLOGY

# L70 TESTING REPORT Energy Star TM-21 Calculation

I M-80 Test Innuts

Issued: 26/7/2019

REV: 00 PAG: 1



### TM-21 Inputs

#### Instructions

Yellow fields are completed by the user. Fields not used should be left blank. Cyan fields are calculated based on user entries.

First, enter a description of the LED light source tested. Then complete the fields labeled "LM-80 Testing Details". Test duration must be at least 6,000 hours. If only one case temperature data set is to be used (no interpolation), complete only "Tested case temperature 1". For only two case temperature data sets, complete 1 and 2.

Next, further to the right, in the corresponding box(es) for each tested case temperature, enter the test data along with the time (in hours) at which each measurement was taken. Data entered must be normalized then averaged measured data (per TM-21 sections 5.2.1 and 5.2.2).

Enter drive current, in-situ temperature data and the percentage of initial lumens to project to in the fields labeled "In-Situ Inputs".

Results can be tailored to estimate lumen maintenance at a specific time by entering a value (t) in the yellow field.

A complete TM-21 report will

Description of LED Light Source Tested
(manufacturer, model, catalog number)
lodel: CHELA-26W, manufactured by DIMON Technology Ltd

LM-80 Testing Details	
Total number of units tested per case temperatur	e 25
Number of failures:	0
Number of units measured:	25
Test duration (hours):	10600
Tested drive current (mA):	60
Tested case temperature 1 (T <sub>c</sub> , °C):	55
Tested case temperature 2 (T <sub>c</sub> , °C):	85
Tested case temperature 3 (T <sub>c</sub> , °C):	105

Livi-ou rest inputs					
Test Data for 55⁰C Case		Test Data for 85°C Case		Test Data for 105°C Case	
	Temperature		Temperature		Temperature
Time	Lumen Maintenance	Time	Lumen Maintenance	Time	Lumen Maintenance
(hours)	(%)	(hours)	(%)	(hours)	(%)
0	100.00%	0	100.00%	0	100.00%
542	99.80%	542	98.50%	541	97.50%
1010	99.80%	1009	98.40%	1010	97.00%
1699	99.50%	1698	98.20%	1699	96.40%
2372	99.40%	2370	97.90%	2372	95.80%
3124	99.10%	3123	97.60%	3125	95.40%
3812	99.00%	3811	97.60%	3812	95.20%
4520	98.80%	4515	97.30%	4520	94.80%
5185	98.90%	5181	97.20%	5186	94.60%
6019	98.90%	6014	97.20%	6019	94.50%
6780	98.60%	6776	96.80%	6781	94.10%
7577	98.60%	7573	96.80%	7577	94.00%
8411	98.40%	8407	96.50%	8412	93.70%
9239	98.00%	9234	96.10%	9239	93.20%
10074	98.30%	10070	96.30%	10074	93.40%

In-Situ Inputs				
Drive current for each LED package/array/module (mA):	25			
In-situ case temperature (T <sub>c</sub> , °C):	60			
Percentage of initial lumens to project to (e.g. for L <sub>70</sub> , enter 70):	62			
Results				
Time (t) at which to estimate lumen maintenance (hours):	10,070			
Lumen maintenance at time (t) (%):	97.35%			



## TM-21 Report

25 0	Test Condition 2 - 85°C Sample size		Test Condition 3 - 1	us c case
	Sample size	0.5		
0		25	Sample size	25
	Number of failures	0	Number of failures	0
60	DUT drive current used in the test (mA)	60	DUT drive current used in the test (mA)	60
10,600	Test duration (hours)	10,600	Test duration (hours)	10,600
5,185 - 10,074	projection (hour to	5,185 - 10,074	projection (hour to	5,185 - 10,074
55	Tested case temperature (°C)	85	Tested case temperature (°C)	105
693E-06	α	2.362E-06	α	3.087E-06
0.998	В	0.985	В	0.962
281,000	Calculated L70(11k) (hours)	196,000	Calculated L70(11k) (hours)	142,000
>64000	(hours)	>64000	(hours)	>64000
1	10,600 5,185 - 10,074 55 693E-06 0.998 281,000	10,600 10,600 10,074 55 10,074 55 693E-06 0.998 281,000 Reported L70(11k) (hours) Reported L70(11k)	10,600	10,600

Table 2: Interpolation Report (projection based on <i>in-situ</i> temperature entered				
T <sub>s,1</sub> (°C)	55.00			
T <sub>s,1</sub> (K)	328.15			
$\alpha_1$	1.693E-06			
B <sub>1</sub>	0.998			
T <sub>s,2</sub> (°C)	85.00			
T <sub>s,2</sub> (K)	358.15			
$\alpha_2$	2.362E-06			
$B_2$	0.985			
E <sub>a</sub> /k <sub>b</sub>	1.30E+03			
Α	8.997E-05			
B <sub>0</sub>	0.991			
T <sub>s,i</sub> (°C)	60.00			
T <sub>s,i</sub> (K)	333.15			
$\alpha_{i}$	1.797E-06			
Projected	261,000			
L70(11k) at 60°C Reported				
L70(11k) at 60°C	>64000			

Report Generated By: Fish Tan	Notes:
Company: DIMON Technology Limited	
Date: July.26, 2019	